



Collano® RS 8500 range



Collano® RS 8500

High quality, elastic, 2C adhesive

Colour

Component A: Light beige
Component B: Black
Mixture: Dark grey

Range of applications

- Metal construction and sheet metal fabrication
- Bodywork, vehicle and ship construction
- Façade elements/panels
- Corner joints on aluminium window profiles
- Bonding of glass and plastics in combination with wood, metal and mineral substrates

Processing

- Application temperature
+5 °C to +40 °C
- Temperature resistance
-40 °C to +110 °C
- Gel time
20–30 minutes at 20 °C
- Fixation time
60–90 minutes at 20 °C
- Final strength
Fully hardened after 24 hours at 20 °C.
Adhesive properties are achieved fully and permanently after 21 days.

Technical data sheets

Immediately obtainable from: www.collano.com



Collano® RS 8505

High quality, elastic, 2C adhesive with long open time

Colour

Component A: Light beige
Component B: Black
Mixture: Dark grey

Range of applications

- Metal construction and sheet metal fabrication
- Bodywork, vehicle and ship construction, containers
- Façade elements/panels
- Bonding of glass and plastics in combination with wood, metal and mineral substrates

Processing

- Application temperature
+5 °C to +40 °C
- Temperature resistance
-40 °C to +110 °C
- Gel time
Approx. 60 minutes at 20 °C
- Fixation time
150–180 minutes at 20 °C
- Final strength
Fully hardened after 24 hours at 20 °C.
Adhesive properties are achieved fully and permanently after 21 days.



Collano® RS 8507

High quality, elastic, 2C adhesive with defined bond line thickness

Colour

Component A: Light beige
Component B: Black
Mixture: Dark grey

Range of applications

- Metal construction and sheet metal fabrication
- Bodywork, vehicle and ship construction, containers
- Façade elements/panels
- Defined adhesive joint thickness
0.5 – 0.7 mm

Processing

- Application temperature
+5 °C to +40 °C
- Temperature resistance
-40 °C to +110 °C
- Gel time
Approx. 60 minutes at 20 °C
- Fixation time
150–180 minutes at 20 °C
- Final strength
Fully hardened after 24 hours at 20 °C.
Adhesive properties are achieved fully and permanently after 21 days.

Collano Adhesives AG, CH-6203 Sempach-Station
Switzerland, Phone +41 41 469 91 11, Fax +41 41 469 91 12
collano@collano.com, www.collano.com